

PRODUCT DATA SHEET

Sikagard[®]-720 EpoCem[®] IN

3-part cement and epoxy combination micro mortar for surface sealing

DESCRIPTION

Sikagard[®]-720 EpoCem[®] IN is a three-part, epoxy modified cementitious, thixotropic, fine textured mortar for levelling and finishing of concrete, mortar or stone surfaces.

USES

- As a levelling layer over concrete and mortars in 1 - 3 mm on vertical or horizontal surfaces,
- Application in new works or damaged concrete repairs, in aggressive chemical environments
- Application over high moisture content substrates, even green concrete
- As a Temporary Moisture Barrier (TMB) (min. 2 mm thick) under Epoxy, Polyurethane and PMMA* resin coatings requiring dry substrates, for a lasting solution.
- As a pore sealer for the re-profiling, smoothing and levelling of concrete surfaces
- In the food industry, as a levelling and smoothing layer for walls and covings, prior to the application of a suitable Sika[®] epoxy or PUR finish

- Suitable for moisture control (Principle 2, method 2.3 of EN 1504-9)
- Suitable for restoration work (Principle 3, method 3.1 and 3.3 of EN 1504-9).
- Suitable for physical resistance (Principle 5, method 5.1 of EN 1504-9)
- Suitable for preserving or restoring passivity (Principle 7, method 7.1 and 7.2 of EN 1504-9)
- Suitable for increasing resistivity (Principle 8, method 8.3 of EN 1504-9)

FEATURES

- Improved chemical resistance compared to PCC mortar
- Excellent protection of concrete in aggressive environments
- Easy and fast application
- Impervious to liquids but permeable to water vapour
- Excellent bond to green or hardened concrete whether damp or dry
- Fast overcoating of Sika[®] resin-based finish products
- Ideal preparation for smooth surface finishes
- For internal or external use
- Contains no solvents
- Can be applied by hand or mechanically by spray pump machine

PRODUCT INFORMATION

Composition	Epoxy modified cementitious mortar	
Packaging	Part A+B+C Pre-batched	18.50 kg x 2 sets
	Part A	1.00 kg plastic container
	Part B	2.50 kg plastic container
	Part C	15.0 kg bag
Appearance and colour	Part A	White liquid
	Part B	Translucent yellowish liquid
	Part C	Cement grey powder
	Part A+B+C mixed	Grey

Shelf life	6 months from date of production	
Storage conditions	Store in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +40°C. Part A, Part B: Protect from frost Part C: Protect from humidity	
Density	Part A	~1.08 kg/L
	Part B	~1.01 kg/L
	Part C	~1.155 kg/L (Bulk density)
	Part A+B+C mixed	~2.01 kg/L
All density values at +30°C		

TECHNICAL INFORMATION

Compressive strength	1 day	≥ 20 N/mm ²	(ASTM C 579)
	3 days	≥ 25 N/mm ²	(IS 9162-1979)
	7 days	≥ 30 N/mm ²	
	14 days	≥ 40 N/mm ²	
Curing temperature +27° C			
Tensile adhesion strength	> 4 N/mm ² (after 7 days at +27° C)		(DIN EN 1542)
Service temperature	0°C to +80°C for continuous exposure.		

APPLICATION INFORMATION

Mixing ratio	Part A : Part B : Part C = 2 : 5 : 30 (by weight)										
Consumption	Primer: Water dependent on substrate absorbency. Screed / Mortar / Render: ~2.0 kg/m ² /mm This figure is theoretical and does not include for any additional material required due to surface porosity, surface profile, variations in level or wastage, etc.										
Layer thickness	Minimum	1 mm									
	Maximum	3 mm									
	Special cases - Isolated and confined small areas (< 0.01 m ²)	upto 5 mm									
Ambient air temperature	+10°C min. / +40°C max.										
Relative air humidity	20% min. / 80% max										
Substrate temperature	+10°C min. / +40°C max.										
Pot Life	~35 minutes (100 g mass at +27°C)	(FIP 5.1)									
Waiting time to overcoating	Once Sikagard®-720 EpoCem® IN is tack free it is possible to apply vapour permeable seal coats. For the application of vapour tight coatings on Sikagard®-720 EpoCem® IN, allow the surface moisture to fall below 4%, not earlier than: <table border="1" data-bbox="606 1624 1430 1758"> <thead> <tr> <th>Substrate Temperature</th> <th>Waiting Time</th> </tr> </thead> <tbody> <tr> <td>+10°C</td> <td>~60 hrs</td> </tr> <tr> <td>+20°C</td> <td>~15 hrs</td> </tr> <tr> <td>+30°C</td> <td>~8 hrs</td> </tr> </tbody> </table>			Substrate Temperature	Waiting Time	+10°C	~60 hrs	+20°C	~15 hrs	+30°C	~8 hrs
Substrate Temperature	Waiting Time										
+10°C	~60 hrs										
+20°C	~15 hrs										
+30°C	~8 hrs										
Note: Times are approximate at 75% R.H. and will be affected by changing ambient and substrate conditions, particularly temperature and relative humidity.											
Curing treatment	Applied Product ready for use										

Temperature	Full cure
+15°C	~ 14 days
+25°C	~ 7 days
+35°C	~ 4 days

Note: All cure times are approximate and will be affected by changing substrate and ambient conditions.

Setting time	Temperature	Full Cure
	+15°C	~14 days
	+25°C	~7 days
	+35°C	~4 days

All cure times are approximate and will be affected by changing substrate and ambient conditions.

SYSTEM INFORMATION

System structure

The system configuration as described must be fully complied with and may not be changed.

Primer as indicated below is suitable for each of these substrates:

- Green concrete (as soon as mechanical preparation is possible)
- Damp concrete (> 14 days old)
- Damp aged concrete (rising moisture)

Vertical or horizontal pore filling, repair and levelling:

Layer thickness	1 - 3 mm
Primer	Water saturation with matt, damp appearance
Render	Sikagard®-720 EpoCem® IN
Top coating	can be left un-coated or suitable product from the Sikafloor® and Sikagard® range can be used as soon as the surface humidity of Sikagard®-720 EpoCem® IN has reached 4%

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Static Cracks

Prefill and level with Sikadur® or Sikafloor® epoxy resin

Dynamic Cracks (> 0.4 mm)

To be assessed on site and if necessary apply a stripe coat of elastomeric material or design as a movement joint

IMPORTANT CONSIDERATIONS

- Always ensure good ventilation when using Sikagard®-720 EpoCem® IN in a confined space, to remove excess moisture.
- Freshly applied Sikagard®-720 EpoCem® IN must be protected from damp, condensation and water for at least 24 hours.
- For external applications, apply primer and Sikagard®-720 EpoCem® IN on a falling temperature. If applied during rising temperatures "pin holing" can occur.
- Non moving construction joints require pre-treatment with a stripe coat of primer and Sikagard®-720 EpoCem® IN. Treat as follows:

- The incorrect assessment and treatment of cracks can lead to a reduced service life and reflective cracking.

- Colour variations can occur on unsealed Sikagard®-720 EpoCem® IN through exposure to direct sun light. This however, will not influence the mechanical properties.
- When overlaying with PMMA screeds, the surface of Sikagard®-720 EpoCem® IN must be fully broadcast with sand 0.4 - 0.7 mm.
- The TMB effect in Sikagard®-720 EpoCem® IN is limited in time, without additional preparation.
- Always verify the surface moisture content if more than 5 - 7 days have passed since application.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The concrete substrate must be sound and of sufficient compressive strength (minimum 20 N/mm²) with a minimum pull off strength of 1.5 N/mm². The substrate can be damp but must be free of standing water and free of all contaminants such as oil, grease, coatings and surface treatments, etc.

SUBSTRATE PREPARATION

Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface. Weak concrete must be removed and surface defects such as blow holes and voids must be fully exposed. Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, Sikadur® and Sikagard® range of materials. High spots can be removed by grinding. All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

MIXING

Prior to mixing, shake part A (white liquid) briefly until homogenous, then pour into the container of part B and shake vigorously for at least 30 seconds. When dosing out of drums, stir and homogenize first. Pour the mixed binder (A+B) into a suitable mixing container (capacity of about 30 litres) and gradually add part C while stirring with a power mixer. Mix thoroughly for 3 minutes until a uniform mix has been achieved.

MIXING TOOLS

Mix using a slow speed electric mixer (300 - 400 rpm) with helical paddle or other suitable equipment. For mixing 2–3 bags at once, single or counter rotating double mortar (basket type) and forced action (pan type) mixers are also suitable. Free fall mixers must not be used.

APPLICATION

Hand application:

Place mixed Sikagard®-720 EpoCem® IN onto the matt-damp substrate and spread evenly to the required thickness with a trowel or spatula. When necessary, it may be finished with a moist neoprene sponge or brush.

Mechanical application:

Application on to the surface can also be done using hopper gun or wet spray technique. For example an Aliva Hopper gun, a Putzmeister S-5 or a Graco T-Max 405. Subsequent finishing by hand is required. Do not use additional water, which would disturb the surface finish and cause discolouration. Freshly applied Sikagard®-720 EpoCem® IN must be protected from rain for at least 24 hours. Once Sikagard®-720 EpoCem® IN is tack free it is possible to apply vapour permeable seal coats. Always verify that surface moisture < 4% when applying vapour tight coatings. A seamless finish can be achieved if a “wet” edge is maintained during application.

Note:

Sikagard®-720 EpoCem® IN can be applied on green or damp concrete, without any standing water. Although the product can be applied onto green concrete surfaces (> 24 hours), it is advised to allow at least 3 days for early shrinkage of concrete to occur in order to prevent concrete shrinkage cracks from appearing on the screed/render surface.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Bangladesh Limited

Impetus Center, 242/B, (8th Floor),
Bir Uttam Mir Shawkat Sarak,
(Tejgaon-Gulshan Link Road),
Dhaka -1208, Bangladesh.
Tel +880 1313095060, +880 1313095061
<https://bgd.sika.com/>

Product Data Sheet

Sikagard®-720 EpoCem® IN
December 2025, Version 02.01
020302050070000009

Sikagard-720EpoCemIN-en-BD-(12-2025)-2-1.pdf

