

# PRODUCT DATA SHEET

## Sikagard®-62

### 2-PART EPOXY PROTECTIVE COATING

#### DESCRIPTION

Sikagard®-62 is a two part, rigid, 100 % solids, coloured high build epoxy resin based protective coating.

#### USES

Sikagard®-62 is a construction products which only should be applied by trained applicators.

- Chemical resistant protective layer on concrete, stone, cementitious mortars and renderings, epoxy cement, epoxy resin based products and steel
- Lining in storage tanks and silos
- Anti-corrosion coating on steel in food processing plants, sewage works, farms, agricultural enterprises, chemical and pharmaceutical facilities and beverage industry

#### CHARACTERISTICS / ADVANTAGES

- Hard surfaces – excellent abrasion resistance
- Excellent adhesion to concrete, masonry and steel surfaces

#### PRODUCT INFORMATION

Composition	Epoxy resin	
Packaging	Part A	9.0 kg set
	Part B	3.0 kg set
Appearance / Colour	RAL 7032 (pebble grey), other on request	
Shelf life	Part A: 12 months	
	Part B: 12 months	
Storage conditions	From date of production if stored properly.	
Storage conditions	The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C. Protected from direct sunlight.	

- Good resistance against wide range of industrial chemicals
- Easy application – simple mixing and application procedures
- Hygienic – impervious finish provides easily cleaned surfaces
- Suitable for contact with food and potable water

#### SUSTAINABILITY

Conformity with LEED v2009 IEQc 4.2: Low-Emitting Materials - Paints and Coatings

#### APPROVALS / CERTIFICATES

- Coating for concrete protection according the requirements of EN 1504-2:2004, Declaration of Performance 0206060100100000011008, certified by FPC Notified Body and provided with CE marking
- WRAS, test report No. M104991, 2011, Contact with water for wholesome purposes according BS 6920-1:2000

Density	Part A	~1.45 kg/l	(EN ISO 2811-1)
	Part B	~1.02 kg/l	
Mixed resin ~1.37 kg/l Density values determined at +23°C			
Solid content	~ 100 %		

## TECHNICAL INFORMATION

Shore D Hardness	~80	(DIN 5305)		
Mechanical Resistance	Taber Abraser	CS 10/ 1000/ 1000	24.4 mg	(ASTM D 4060)
	Taber Abraser	CS 17/ 1000/ 1000	70 mg	
	Taber Abraser	H 22/ 1000/ 1000	560.6 mg	
Tensile Adhesion Strength	> 1.5 N/mm <sup>2</sup> to concrete		(ISO 4624)	
Chemical Resistance	Please contact Sika technical service for specific information.			
Temperature Resistance	<b>Exposure</b>	<b>Dry heat</b>		
	Permanent	+50°C		
	max. 7 days	+80°C		
	max. 12 hours	+100°C		

## APPLICATION INFORMATION

Mixing Ratio	Part A : Part B = 3 : 1 by weight			
Consumption	~0.30 kg/m <sup>2</sup> per layer (min. recommendation is two layers or depend consumption required)			
Layer Thickness	~0.2 mm per layer (min. recommendation is two layers or depend thickness required)			
Ambient Air Temperature	+8°C min. / +40°C max.			
Relative Air Humidity	< 80 %			
Substrate Temperature	+8°C min. / +40°C max. Minimum 3°C above dew point, beware of condensation			
Pot Life	<b>Temperature</b>	<b>Time</b>		
	+10°C	~30 min		
	+20°C	~20 min		
	+30°C	~10 min		
Curing Time	At +20 °C,			
	Touch dry	3 hours		
	Top coat	16 hours		
	Full cure	7 days		
Waiting Time / Overcoating	<b>Temperature</b>	<b>Min.</b>	<b>Max.</b>	<b>Full cure</b>
	+10°C	~ 30 hours	~ 3 days	~ 14 days
	+20°C	~ 10 hours	~ 2 days	~ 10days
	+30°C	~ 6 hours	~ 1 day	~ 5 days

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

The substrate must be sound, clean, dry, free from contaminants such as dirt, grease, oil, old coatings, release agents, laitance and other adhesion preventing or influencing substances.

On high absorbent, non-sound, contaminated, not ce-

ment based substrates precautions have to be taken and a suitable primer has to be used.

## SUBSTRATE PREPARATION

### Concrete Substrate

Concrete substrate must be prepared mechanically to achieve an open textured surface.

Weak areas in the substrate must be removed and surface defects such as blowholes and voids must be fully exposed.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

Open voids and blowholes need to be closed with a suitable Sika® pore filling mortar. The roughness of the substrate needs to be levelled with a suitable Sika® rendering and levelling mortar.

### Steel Surface

Steel surface must be prepared mechanically using abrasive blast cleaning. The level SSPC-SP 10 "near white metal blast cleaned" or level Sa 2 ½ according to ISO EN 12944-4 has to be achieved. Welds and joints have to be prepared according to EN 14879, part 1. After blast cleaning remove all dust dirt and blasting material. In order to maintain the surface conditions after blast cleaning air-conditioning is recommended.

## MIXING

Prior to mixing stir part A mechanically. When all of part B has been added to part A mix continuously for 3 minutes until a uniform mix has been achieved. Use a low speed electrical stirrer (300–400 rpm) to avoid air entrapment. To ensure proper mixing pour material into a clean container and stir again.

## APPLICATION

Apply by brush, roller or airless spray.

## CLEANING OF EQUIPMENT

Clean all tools with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

## IMPORTANT CONSIDERATIONS

- Do not apply Sikagard®-62 on moist substrates
- Sag resistance on vertical surface is approx. 200 µm.
- Freshly applied Sikagard®-62 must be protected from damp, condensation and water for at least 24 hours
- For exact colour matching ensure using material from the same control batch numbers.

### SIKA BANGLADESH LIMITED

SkyLark MAK 84, 8th floor  
House No. 84, Block D, Road No. 11  
Banani, Dhaka-1213, Bangladesh  
Phone 1: +88 01313095060  
Phone 2: +88 01313095061  
ind.sika.com

### Product Data Sheet

Sikagard®-62  
January 2020, Version 04.01  
020606010010000001

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## DIRECTIVE 2004/42/CE LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type sb) is 550 / 500 g/l (Limits 2007 / 2010) for the ready to use product. The maximum content of Sikagard®-62 is < 500 g/l VOC for the ready to use product.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sikagard-62-en-BD-(01-2020)-4-1.pdf