

PRODUCT DATA SHEET

Sika® ViscoCrete®-3006 ES (Rossem)

High Performance Superplasticizing Admixture

DESCRIPTION

Imparts very high workability, workability retention and allows a large reduction in water content and gives high early strength.

USES

Sika® ViscoCrete®-3006 ES (Rossem) a superplasticizer for free-flowing concrete in floors, slabs, foundations, slender components with dense reinforcement, walls and columns and other structural elements.

Sika® ViscoCrete®-3006 ES (Rossem) is mainly used for the following types of concrete:

- High performance concrete
- High strength concrete
- Ready mixed concrete
- Self compacting concrete
- Precast concrete
- Pre stressed concrete
- Pumped concrete

FEATURES

Sika® ViscoCrete®-3006 ES (Rossem) produces a more uniformly cohesive high quality free flowing concrete. Sika® ViscoCrete®-3006 ES (Rossem) will result in the following advantages of concrete:

- Improved dispersion properties
- Very high water reduction
- Improved strength and density
- Improved water tightness
- Improved durability
- Improved cohesion properties
- Improved rheology
- Improved flowability
- Reduced drying shrinkage
- Improved workability retention
- Water reduction up to 25-35 % depending on dosage*
- 28 days strength improved by up to 40 %*

* This will depend on dosage and mix design

CERTIFICATES AND TEST REPORTS

IS 9103, ASTM C494 Type C, E & F, EN 934-2 T 12

PRODUCT INFORMATION

Composition	Aqueous solution of modified poly carboxylate
Packaging	230 kg HDPE carboy
Appearance and colour	Light Brown Liquid
Shelf life	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.
Storage conditions	Store in dry conditions at temperatures between +10°C and +40°C. Protect from direct sunlight and frost.
Density	~1.09 kg/l at 25°C
pH-Value	≥ 6
Total chloride ion content	Nil

Product Data Sheet

Sika® ViscoCrete®-3006 ES (Rossem)

December 2025, Version 01.03

021301011000003708

APPLICATION INFORMATION

Recommended dosage	Standard dosage will vary from 0.7% to 1.5% by weight of cement. Exact dosage rates are dependent on the quality of cement, aggregates, water/cement ratio and ambient temperature. Therefore, in many cases it is advisable to carry out trial mixes. Higher dosage may be used if agreed by engineer and consultant. Stir well before use.
Compatibility	Sika® ViscoCrete®-3006 ES (Rossem) may be combined with many other Sika® Products. Compatible with all types of cements and cementitious materials. Important: Always conduct trials before combining products in specific mixes and contact our Technical Service Department for information about specific combinations.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTATION

Excessive water addition or overdosing may cause bleeding or segregation.
If frozen and / or if precipitation has occurred, Sika® ViscoCrete®-3006 ES (Rossem) may be used after thawing slowly at room temperature and after intensive mixing.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

DISPENSING

Sika® ViscoCrete®-3006 ES (Rossem) can be added into the mixing water or directly into the concrete mixer after 50 – 70% of the mixing water has been added. The addition of Sika® ViscoCrete®-3006 ES (Rossem) to dry aggregate or cement is not recommended.
To achieve optimum performance a minimum wet mixing time, which is depending on the mixing conditions and the mixer performance, of 60 seconds is recommended.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

Dhaka -1208, Bangladesh.

1311450610 1313095061
<https://bgd.sika.com/>

LEGAL NOTES

The information, and, in particular, the recommenda-

tions relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaViscoCrete-3006ESRossem-en-BD-(12-2025)-1-3.pdf