

## PRODUCT DATA SHEET

# Sika® ViscoCrete®-3064 ES BD

### HIGH PERFORMANCE SUPERPLASTICIZING ADMIXTURE

#### DESCRIPTION

Imparts very high workability, workability retention and allows a large reduction in water content and gives high early strength.

#### USES

Sika® ViscoCrete®-3064 ES BD a superplasticizer for free flowing concrete in floors, slabs, foundations, slender components with dense reinforcement, walls and columns and other structural elements.

Sika® ViscoCrete®-3064 ES BD is mainly used for the following types of concrete:

- High performance concrete
- High strength concrete
- Ready mixed concrete
- Self compacting concrete
- Precast concrete
- Prestressed concrete
- Pumped concrete

#### CHARACTERISTICS / ADVANTAGES

Sika® ViscoCrete®-3064 ES BD produces a more uniformly cohesive high quality free flowing concrete. Sika® ViscoCrete®-3064 ES BD will result in the following advantages of concrete:

- Improved dispersion properties
- Very high water reduction
- Improved strength and density
- Improved durability
- Improved cohesion properties
- Improved water tightness
- Improved rheology
- Improved flowability
- Reduced drying shrinkage
- Improved workability retention
- Water reduction up to 25-35 % depending on dosage\*
- High strength development after 14 hours
- 28 days strength improved by up to 40 %\*

\* This will depend on dosage and mix design

#### APPROVALS / CERTIFICATES

IS 9103, ASTM C494 Type F, EN 934-2 T 12

#### PRODUCT INFORMATION

<b>Composition</b>	Improved Poly Carboxylate Ether
<b>Packaging</b>	230 kg HDPE carboy
<b>Shelf life</b>	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.
<b>Storage conditions</b>	Store in dry conditions at temperatures between +10°C and +40°C. Protect from direct sunlight and frost.
<b>Appearance and colour</b>	Dark Brown Liquid
<b>Density</b>	~1.09 kg/l at 25°C
<b>pH-Value</b>	≥ 6

# APPLICATION INFORMATION

## Recommended dosage

Standard dosage will vary from 0.5% to 1.5% by weight of cement. Exact dosage rates are dependent on the quality of cement, aggregates, water/cement ratio and ambient temperature. Therefore, in many cases it is advisable to carry out trial mixes.  
Higher dosage may be used if agreed by engineer and consultant.  
Stir well before use.

## Compatibility

Sika® ViscoCrete®-3064 ES BD may be combined with many other Sika® Products.  
Compatible with all types of cements and cementitious materials.  
Important: Always conduct trials before combining products in specific mixes and contact our Technical Service Department for information about specific combinations

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

Excessive water addition or overdosing may cause bleeding or segregation.  
If frozen and / or if precipitation has occurred, Sika® ViscoCrete®-3064 ES BD may be used after thawing slowly at room temperature and after intensive mixing.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### DISPENSING

Sika® ViscoCrete®-3064 ES BD can be added into the mixing water or directly into the concrete mixer after 50 – 70% of the mixing water has been added. The addition of Sika® ViscoCrete®-3064 ES BD to dry aggregate or cement is not recommended.  
To achieve optimum performance a minimum wet mixing time, which is depending on the mixing conditions and the mixer performance, of 60 seconds is recommended.

### SIKA BANGLADESH LIMITED

Skylark MAK 84, 8th floor  
House No. 84, Block D, Road No. 11  
Banani, Dhaka-1213, Bangladesh  
Phone 1: +88 01313095060  
Phone 2: +88 01313095061  
ind.sika.com

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaViscoCrete-3064ESBD-en-BD-(01-2022)-1-3.pdf

### Product Data Sheet

Sika® ViscoCrete®-3064 ES BD  
January 2022, Version 01.03  
021301011000003707