

## PRODUCT DATA SHEET

## SikaPlast®-2036 NS BD

High efficient superplasticizer

## DESCRIPTION

SikaPlast®-2036 NS BD is the latest development of superplasticizer for concrete. It meets the requirements for high range water reducing superplasticizers

## USES

SikaPlast®-2036 NS BD is a unique multipurpose superplasticiser that is particularly suitable for the production of ready mixed concrete. Additionally it provides high water reduction and improved fresh concrete characteristics.

With its outstanding cost / performance SikaPlast®-2036 NS BD is used for the following:

- A wide range of applications where excellent workability is requested
- Concrete with high water reduction
- High efficient concrete applications

## FEATURES

SikaPlast®-2036 NS BD is a powerful superplasticiser based on advanced technology which gives the following advantages:

- Strong water reduction, resulting in high density, high strength and reduced Permeability
- Less sensitive against variations in aggregates and / or different cement types
- High efficiency even at low dosage rates
- Extended workability in conjunction with subsequent strength development
- Superior plasticising effect, resulting in improved flow, placing and compaction Characteristics

## CERTIFICATES AND TEST REPORTS

Complies with IS 9103, ASTM C494 Type B,D & G, EN 934-2 T 11.1/11.2

## PRODUCT INFORMATION

Composition	Modified Poly-Carboxylate Ether (PCE)
Packaging	SikaPlast®-2036 NS BD is supplied in 230 Kg, 1000 Kg or bulk on request
Appearance and colour	Light brown liquid
Shelf life	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.
Storage conditions	Store in dry conditions at temperatures between +10°C and +40°C. Protect from direct sunlight and frost.
Density	~1.09 kg/l at 25°C
pH-Value	≥ 6
Total chloride ion content	Nil

## APPLICATION INFORMATION

<b>Recommended dosage</b>	Standard dosage will vary from 0.5% to 2.0% by weight of cement. Exact dosage rates are dependent on the quality of cement, aggregates, water/cement ratio and ambient temperature. Therefore, in many cases it is advisable to carry out trial mixes. Higher dosage may be used if agreed by engineer and consultant. Stir well before use.
<b>Compatibility</b>	SikaPlast®-2036 NS BD may be combined with many other Sika® products. Compatible with all types of cements and cementitious materials. Important: Always conduct trials before combining products in specific mixes and combinations.
<b>Dispensing</b>	SikaPlast®-2036 NS BD is added to the gauging water or added with it into the concrete mixer. To take advantage of the high water reduction, a wet mixing time, which is depending on the mixing conditions and mixer performance, of at least 60 seconds is recommended. To avoid excess water in the concrete, the final dosage must begin only after 2/3 of the wet mixing time.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

When using SikaPlast®-2036 NS BD a suitable mix design has to be taken into account and local material sources shall be trialled.

SikaPlast®-2036 NS BD shall not be added to dry cement.

Excessive water addition or overdosing may cause bleeding or segregation.

### **Frost:**

If frozen and / or if precipitation has occurred, SikaPlast®-2036 NS BD may be used after thawing slowly at room temperature followed by intensive remixing.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

### **SIKA BANGLADESH LIMITED**

Impetus Center, 242/B, 8th Floor  
Bir Uttam Mir Shawkat Sarak  
Dhaka-1208, Bangladesh  
Phone 1: +88 01313095060  
Phone 2: +88 01313095061  
bgd.sika.com

## APPLICATION INSTRUCTIONS

### **APPLICATION METHOD / TOOLS**

The standard rules of good concreting practice, concerning production and placing, are to be followed. Laboratory trials shall be carried out before concreting on site, especially when using a new mix design or producing new concrete components.

Fresh concrete must be cured properly and curing applied as early as possible.

### **CLEANING OF EQUIPMENT**

Clean all tools and application equipment with water immediately after use.

Hardened / cured material can only be mechanically removed.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaPlast-2036NSBD-en-BD-(09-2025)-1-1.pdf

### **Product Data Sheet**

SikaPlast®-2036 NS BD

September 2025, Version 01.01  
021301011000242050