

PRODUCT DATA SHEET

Sika MonoTop®-412 MY

STRUCTURAL REPAIR MORTAR FOR HAND PLACED / WET SPRAY

DESCRIPTION

Sika MonoTop®-412 MY is a single component, fibre reinforced, low shrinkage structural repair mortar. Fast repairs to overhead, horizontal or vertical concrete or mortar surfaces above and below ground level.

USES

- Fast repairs to overhead, horizontal or vertical concrete or mortar surfaces above and below ground level.
- Suitable for restoration work. Repair of spalling and damaged concrete in buildings, bridges, infrastructure and superstructure works
- Suitable for structural strengthening. Increasing the bearing capacity of the concrete structure by adding mortar
- Suitable for preserving or restoring passivity. Increase cover with additional mortar and replace contaminated or carbonated concrete

CHARACTERISTICS / ADVANTAGES

- Superior workability
- Suitable for hand and machine application
- Can be applied up to 50 mm thick per application layer
- Structural repair
- Very low shrinkage behaviour
- Does not require a bonding primer even when manually applied (for static load only)
- Low permeability

APPROVALS / CERTIFICATES

Sika MonoTop®-412 MY complies with R4 class specifications according to EN 1504-3 that are relevant for tropical countries. Test report No. MIS 080/13/R 0753

PRODUCT INFORMATION

Packaging	25 kg bag		
Appearance / Colour	Grey powder		
Shelf life	6 months from date of production		
Storage conditions	Store properly in undamaged original sealed packaging, in dry conditions. Protect from moisture and rain.		
Density	Fresh mortar density: ~2.10 kg/l		
Maximum Grain Size	2.2 mm		
Soluble Chloride Ion Content	Test Result	Class R4 requirement	(EN 1015-17)
	0.011 %	≤ 0.05 %	

TECHNICAL INFORMATION

Compressive Strength	1 day	$\geq 20 \text{ N/mm}^2$	(EN 12190)	
	7 days	$\geq 40 \text{ N/mm}^2$		
At 28 days:				
	Test Result	Class R4 requirement	(EN 12190)	
	52 N/mm ²	$\geq 45 \text{ N/mm}^2$		
Modulus of Elasticity in Compression	Test Result	Class R4 requirement	(EN 13412, Method 2)	
	24.9 GPa	$\geq 20 \text{ GPa}$		
Tensile Strength in Flexure	1 day	$\sim 4 \text{ N/mm}^2$	(EN 12190)	
	7 days	$\sim 7 \text{ N/mm}^2$		
	28 days	$\sim 9 \text{ N/mm}^2$		
Tensile Adhesion Strength	Test Result	Class R4 requirement	(EN 1542)	
	2.8 N/mm ²	$\geq 2.0 \text{ N/mm}^2$		
Restrained Shrinkage / Expansion	Test Results	Class R4 requirement	(EN 12617-4, clause 7)	
	Control Value	2.65 N/mm ²		$\geq 2 \text{ N/mm}^2$
	Restrained Drying Shrinkage	2.38 N/mm ²		$\geq 2 \text{ N/mm}^2$
	Restrained Expansion	2.31 N/mm ²		$\geq 2 \text{ N/mm}^2$
Baenziger Block	No cracks with Baenziger Block Test			
Thermal Compatibility	Test Result	Class R4 requirement	(EN 13687-2)	
	Control Value	2.74 N/mm ²		$\geq 2 \text{ N/mm}^2$
	Thunder Shower for 10 cycles	2.19 N/mm ²		$\geq 2 \text{ N/mm}^2$
	Thunder Shower for 30 cycles	2.07 N/mm ²		$\geq 2 \text{ N/mm}^2$
Capillary Absorption	Test Result	Class R4 requirement	(EN 13057)	
	0.271 kg/m ² .h ^{0.5}	$\leq 0.5 \text{ kg/m}^2.\text{h}^{0.5}$		
Carbonation Resistance	dk_{mean} for test specimen	dk_{mean} for control specimen	(EN 13295-17)	
	4.35	4.50		dk _{mean} for test specimen < dk _{mean} for control specimen

SYSTEMS

System Structure	Sika MonoTop®-412 MY complies with the R4 class specifications according to EN 1504-3 that are relevant for tropical countries (tests carried out at 25–30 °C).		
	Sika MonoTop®-412 MY is part of the range of Sika mortars comprising of:		
	Bonding primer / Corrosion Protection		
	Sika MonoTop®-610 MY	Normal use	
	SikaTop® Armatec® 110 EpoCem®	Demanding requirements	
	Repair mortar		
	Sika MonoTop®-412 MY	Structural hand & machine applied repair mortar	

APPLICATION INFORMATION

Mixing Ratio	3.5–4.0 L of water for 25 kg powder
Consumption	Depends on the substrate roughness and thickness of layer applied. As a guide, ~19 kg of powder per cm thick per m ²
Yield	1 bag yields approximately 13.7 L of mortar
Layer Thickness	6 mm min. / 50 mm max.
Ambient Air Temperature	+6 °C min. / +40 °C max.
Substrate Temperature	+6 °C min. / +40 °C max.
Pot Life	~30 minutes at +23 °C

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete

The concrete shall be free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials. Delaminated, weak, damaged and deteriorated concrete and where necessary sound concrete shall be removed by suitable means.

Steel reinforcement

Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion shall be removed. Surfaces shall be prepared using abrasive blast cleaning techniques or high pressure water-blasting to SA 2 (ISO 8501-1).

Bonding primer

On a well prepared and roughened substrate a bonding primer is generally not required. When a bonding primer is not required pre-wet the substrate to saturated-surface-dry condition. The surface shall not be allowed to dry before application of the concrete repair mortar. The surface shall achieve a dark matt appearance without glistening and surface pores and pits shall not contain water.

When a bonding primer is necessary apply Sika MonoTop®-610 MY (refer to the relevant Product Data Sheet) or other equivalent product from Sika. The bonding primer shall be applied well into the concrete substrate with a stiff brush.

Reinforcement coating

Where a reinforcement coating is required as a barrier (e.g. in the case of insufficient concrete cover), apply two coats of Sika MonoTop®-610 MY (Refer to the relevant Product Data Sheet) to the entire exposed circumference of the reinforcement.

MIXING

Sika MonoTop®-412 MY can be mixed with a low speed (< 500 rpm) hand-drill mixer fixed to a mixing paddle or using a force-action mixer, 2 to 3 bags or more at once depending the type and size of mixer. In small quantity, Sika MonoTop®-412 MY can also be

mixed manually using a trowel or scrapper in a clean container.

Pour the water in the correct proportion into a clean mixing container. While stirring slowly, add the powder to the water. Mixed thoroughly for a minimum of 3 minutes, until the required consistency.

APPLICATION

Sika MonoTop®-412 MY can be applied either manually using traditional techniques or mechanically using wet spray equipment.

When a bonding primer is required, ensure it is still tacky when the repair material is applied (wet on wet technique). When applied manually, pressed the repair mortar with a trowel, working it well into the substrate.

Finishing for both hand and machine application can be done with the relevant roughcast as soon as the mortar has started to stiffen.

CURING TREATMENT

Protect the fresh mortar immediately from early hydration using a curing compound or wet-hessian.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed.

IMPORTANT CONSIDERATIONS

- Refer to the Method Statement for Concrete Repair using Sika MonoTop® system for more information regarding substrate preparation
- Avoid application under direct sun and/or strong wind
- Do not add additional water than recommended when mixing Sika MonoTop®-412 MY
- Apply only to sound and well prepared substrate
- Do not add additional water during the surface finishing phase as this will cause discoloration and cracking
- Protect freshly applied material from freezing

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA BANGLADESH LIMITED

Skylark MAK 84, 8th floor
House No. 84, Block D, Road No. 11
Banani, Dhaka-1213, Bangladesh
Phone 1: +88 01313095060
Phone 2: +88 01313095061
ind.sika.com

Product Data Sheet
Sika MonoTop®-412 MY
March 2020, Version 01.02
020302040030000167

SikaMonoTop-412MY-en-BD-(03-2020)-1-2.pdf

