

PRODUCT DATA SHEET

Sikalastic®-510 CoolCoat IN

Acrylic based liquid applied membrane for roof waterproofing (Formerly Davco® K10 Sovacryl)

DESCRIPTION

Sikalastic®-510 CoolCoat IN is a 1-part, acrylic, water based, elastic, cold applied liquid membrane that can be applied directly from the container. It provides a seamless, smooth waterproof finish which is resistant to UV exposure, environmental pollution and has elastic and vapour permeable properties.

USES

- Roof waterproofing for new construction and refurbishment projects
- Waterproofing of external walls
- Waterproofing and renovation of old roof tiles
- Roofs with numerous details such as penetrations, drains, roof lights and complex geometry

FEATURES

- Resistant to UV exposure
- Mould and fungus resistant
- Good crack-bridging ability and elongation at break
- Vapour permeable
- Water based
- Low VOC
- 1-part ready to use
- Easy to apply
- Available in various colours
- Cold applied - requires no heat or flame
- Extends the life of old roofs and walls

CERTIFICATES AND TEST REPORTS

Tested at NABL Accredited Lab for upto 7 years Life Expectancy under standard conditions of exposure and application guidelines as per the Product Data sheet

PRODUCT INFORMATION

Composition	Modified acrylic dispersion	
Packaging	25 kg and 5 kg container	
Appearance and colour	Thick viscous liquid / White or Grey Other colours on request subject to minimum order quantity. Important: Applied colours selected from colour charts will be approximate. Important: For colour matching, apply colour sample and confirm selected colour under real lighting conditions.	
Shelf life	12 months from date of production	
Storage conditions	The product must be stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C.	
Density	~1.37 kg/L (+30 °C)	(EN ISO 2811-1)
Solid content by mass	~60 %	

TECHNICAL INFORMATION

Shore A hardness	~70	(ASTM D2240)
Tensile strength	~2 N/mm ²	(ASTM D412)
Tensile strain at break	~100 %	(ASTM D412)
Tensile adhesion strength	≥ 0.5 N/mm ²	(ASTM D4541)
Crack bridging ability	upto 2 mm	(ASTM C836)
Solar reflectance index	SRI ≥ 101	(ASTM E-1980-19)

APPLICATION INFORMATION

Consumption	~1.2–1.5 kg/m² in 2 coats Note: The consumption will vary depending on application area, substrate type, substrate roughness, surface profile, absorption of the surface and thickness required.		
Ambient air temperature	+5 °C min. / +40 °C max.		
Relative air humidity	80 % max.		
Dew point	Beware of condensation. The substrate and uncured applied roof material must be at least +3 °C above dew point to reduce the risk of condensation on the surface finish.		
Substrate temperature	+5 °C min. / +40 °C max.		
Substrate moisture content	≤ 6 % parts by weight. The following test methods can be used: Sika®-Tramex meter, CM-measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).		
Waiting time to overcoating	Base layer	Overcoating layer	Waiting time
	Sikalastic-10 Primer W	Sikalastic®-510 Cool-Coat IN	~30 min
	Sikalastic®-510 Cool-Coat IN	Sikalastic®-510 Cool-Coat IN	~6 h
	Note: Above values are at +30 °C and 50 % relative humidity. Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.		
Applied product ready for use	Light traffic	~24 h	
IMPORTANT Applied Sikalastic®-510 CoolCoat IN must not be subjected to ponding before 7 days. Contact Sika Technical Services and refer to ASTM D5957 for more information.			

SYSTEM INFORMATION

System structure	Layer	Product
	Primer	Sikalastic®-10 Primer W
	Base coat	Sikalastic®-510 CoolCoat IN
	Top coat	Sikalastic®-510 CoolCoat IN
	(Optional) Clear coat	Sikalastic®-10 Primer W

Important: Do not overcoat Sikalastic®-510 CoolCoat IN with tile, concrete or others. Sikalastic®-510 CoolCoat IN is an exposed system.

Important: For larger application areas and high demanding applications, use a glass fabric reinforcement Sika® Fabric-50 between the coats. For normal exposures, usage of Sika® Fabric-50 is optional. Reinforcement

(partial or total) must be used over dynamic cracks and joints.
Important: For enhanced dirt pick up resistance and easy cleanability, above build up must be further coated with a thin layer of Sikalastic®-10 Primer W.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

EQUIPMENT

Substrate Preparation Equipment

- Abrasive blast cleaning / planing / scarifying or grinding equipment
- Manual or mechanical wire brushes
- High pressure power washer

Mixing Equipment

- Electric single paddle mixer (300–400 rpm)

Application Equipment

- Brush: Soft bristle
- Roller: Solvent resistant, “non-fuzzy”

SUBSTRATE QUALITY / PRE-TREATMENT

General

- All dust, loose and friable material must be completely removed from all surfaces before application of the product and associated system products, preferably by industrial vacuuming equipment.
- To confirm adequate surface preparation and Sikalastic®-510 CoolCoat IN adhesion, carry out a small trial before full application together with adhesion tests as required.

Cementitious substrates

- Substrate must be sound with a minimum tensile adhesion strength of 1.5 N/mm², clean, dry and free of all contaminants such as dirt, oil, grease, coatings, laitance, surface treatments and loose friable material.
- New concrete must be cured for at least 28 days and have a tensile strength >1.5 N/mm².
- Substrates must be prepared mechanically using suitable substrate preparation equipment to remove cement laitance and achieve an open textured gripping surface profile suitable for the product thickness.
- High spots can be removed by grinding.
- Weak cementitious substrates must be removed and surface defects such as blow holes and voids must be fully exposed.
- Repairs to the substrate, filling of joints,

blowholes/voids and surface levelling must be carried out using appropriate repair mortars from our Sika® range. Products must be cured before applying Sikalastic®-510 CoolCoat IN.

Brick and stone

- Mortar joints must be sound and preferably flush pointed.
- Use localised Sika® reinforcement over joints.

Ceramic, roof tiles

- Ensure all tiles are securely fixed.
- Replace any broken, loose or missing sections.
- Power wash the surface.

Metal

- Metals must be in a sound surface condition.
- Abrade exposed surfaces to a bright metal finish.
- Use localised Sika® reinforcement over joints and fixings.
- Use Sikalastic®-10 Primer EP with sand flushing to ensure proper adhesion and protect metal from corrosion.

Wood

- Wood and wood-based panel roof decks must be in good structural condition, firmly adhered or mechanically fixed.

Paints/Coatings

- The existing material must be sound and firmly adhered to the substrate.
- Remove any oxidized or loose layers.
- To confirm compatibility with Sikalastic®-510 CoolCoat IN, carry out a small trial before full application.
- For existing Sikalastic®-510 CoolCoat IN coating, power wash to clean the surface.

MIXING

Important: Avoid over-mixing to minimise air entrainment.

Note: Use an electric single or double paddle mixer (300–400 rpm) with spiral paddle for mixing.

- Product is supplied ready for use.
- Before application, mix for at least 1 minute or until the liquid and all the coloured pigment has achieved a uniform colour.

APPLICATION

Important: Protect the coating from damp, condensation and direct water contact for at least 24 hours.

Important: If applied on porous substrates during rising temperatures pin holes may occur from rising air. Apply during falling temperatures.

Important: Do not apply on roofs with improper slopes leading to long ponding.

Important: Do not allow temporary ponding to remain between coats on any horizontal surfaces or until the final coating has totally cured. Brush or mop surface water away during this time.

PRIMER

1. Pour the mixed primer onto the prepared substrate.

2. Apply the product evenly over the surface with a brush or fleece roller. Ensure a continuous pore free coat covers the substrate.
3. Back roll the surface in two directions at right angles with a fleece roller.

ROOF WATERPROOFING

Important: Apply 2 coats at the same consumption.

1. Pour the mixed product onto the prepared substrate (for brush or roller application).
2. Apply the product evenly over the surface with a short pile roller, a brush or airless spray. Note: The consumption is specified in Application Information.
3. (Optional) Wherever coating is to be reinforced with glass fabric, lay Sika® Fabric-50 into the freshly applied base coat and embed firmly into the wet coat with brush. Reinforcement overlaps must be a minimum of 50 mm.
4. After the inter-coat waiting time apply a second coat over the surface with a short pile roller, a brush or airless spray.
5. (Optional) Apply one thin coat of Sikalastic®-10 Primer W for enhanced dirt resistance and cleanability.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with suitable solvent like NC thinner, etc immediately after use. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA BANGLADESH LIMITED

Impetus Center, 242/B, 8th Floor
Bir Uttam Mir Shawkat Sarak
Dhaka-1208, Bangladesh
Phone 1: +88 01313095060
Phone 2: +88 01313095061
bgd.sika.com

Product Data Sheet

Sikalastic®-510 CoolCoat IN
August 2025, Version 02.01
020915108010000027

Sikalastic-510CoolCoatIN-en-BD-(08-2025)-2-1.pdf