

PRODUCT DATA SHEET

SikaCeram[®]-288 H

DEFORMABLE, CEMENT BASE HIGH PERFORMANCE ADHESIVE WITH NO VERTICAL SLIP AND EXTENDED OPEN TIME. C2TE S1 CLASSIFIED ACCORDING TO EN 12004

DESCRIPTION

SikaCeram[®]-288 H is deformable, one-pack adhesive consisting of high resistance cements, high polymer content, selected silicon / quartz mineral charges and specific additives.

It can create deformable adhesive layers up to 15 mm thickness. It is suitable for porcelain and natural stone on façades, heated floors, swimming pools and industrial floors.

USES

- Laying all kind of ceramic, vitrified tiles, including large porcelain
- Laying thin porcelain stoneware slabs, thin tiles, glass mosaic
- Laying marble and natural stone, provided not sensitive to water
- Indoor and outdoor, on walls and floors
- Laying on heated floors, water and electric systems

- Indoor over-tiling applications on old tiles, without primer
- Suitable for applications where high performance is demanded, such as swimming pools, industrial and heavy trafficked floors, façades

CHARACTERISTICS / ADVANTAGES

- Deformability
- No vertical slipping
- Extended open time
- Application upto 15 mm thick

APPROVALS / CERTIFICATES

Deformable, one-pack improved cement base adhesive. Particularly suitable for refined porcelain stoneware and large-sized natural stones. Use on heating floor surfaces, façades, industrial floors and swimming pools. EN12004 class C2TE S1.

PRODUCT INFORMATION

Packaging	25 kg bag
Appearance / Colour	Grey and White powder
Shelf life	12 months from date of production.
Storage conditions	Store properly in undamaged original sealed packaging, in dry cooled conditions.
Density	Grey - 1.23 kg/l (Bulk Density) White - 1.1 kg/l (Bulk Density)

Tensile Adhesion Strength	Value Grey	Value White	Requirement EN 12004	Test Method						
Initial Tensile Bond	2.4 N/mm ²	2.2 N/mm ²	≥ 1.0 N/mm ²	EN 1348						
Tensile Bond after Heat Action	2.1 N/mm ²	1.4 N/mm ²	≥ 1.0 N/mm ²	EN 1348						
Tensile Bond After Water Immersion	2.2 N/mm ²	1.7 N/mm ²	≥ 1.0 N/mm ²	EN 1348						
Transverse deformation	Value Grey	Value White	Requirement EN 12004	Test Method						
Transversal Deformation	In between 2.5 - 5 mm	In between 2.5 - 5 mm	≥ 2.5 mm	EN 12002						
Slip Resistance	Value Grey	Value White	Requirement EN 12004	Test Method						
Slip Resistance	≤ 0.5 mm	≤ 0.5 mm	≤ 0.5 mm	EN 1308						
System Structure	<p>In normal conditions, no primer is required. However, for the following difficult highly absorbent substrates, a primer shall be used:</p> <table border="1"> <thead> <tr> <th>Substrate</th> <th>Primer</th> </tr> </thead> <tbody> <tr> <td>Gypsum Board, Precast & FCB Board or Anhydrite Screed</td> <td>Sikafloor® 80 Primer</td> </tr> <tr> <td>PVC, linoleum and old vinyl floors</td> <td>Sikafloor® 80 Primer</td> </tr> </tbody> </table> <p>Application and consumption details of the primer are given in the relevant Product Data Sheet.</p>				Substrate	Primer	Gypsum Board, Precast & FCB Board or Anhydrite Screed	Sikafloor® 80 Primer	PVC, linoleum and old vinyl floors	Sikafloor® 80 Primer
Substrate	Primer									
Gypsum Board, Precast & FCB Board or Anhydrite Screed	Sikafloor® 80 Primer									
PVC, linoleum and old vinyl floors	Sikafloor® 80 Primer									
Mixing Ratio	<p>~7.25-7.75 litres of water (29% - 31%) for 25 kg of SikaCeram®-288 H Grey ~8.25-8.75 litres of water (33% - 35%) for 25 kg of SikaCeram®-288 H White</p>									
Consumption	<p>The consumption is dependent on the surface profile and roughness of the substrate as well as on the size of the tiles and the application technique (double-spreading, in thin-bed consistency, or single-Spreading, in flow-bed consistency). As a guide, in kilograms of powder per m² : 1.2 kg / m² /mm of thickness</p>									
Layer Thickness	15 mm max									
Ambient Air Temperature	+5°C min; +35°C max									
Substrate Temperature	+5°C min; +35°C max									
Pot Life	~3-4 hours at 23°C									
Open Time	~30 minutes at 23°C			(EN 1346)						
Adjustability Time	~40 minutes at 23°C									
Curing Time	Applied product ready for use:									
	Before floor grouting - light foot Traffic	24-36 hours								
	Before wall grouting	4- 6 hours								

SUBSTRATE QUALITY / PRE-TREATMENT

- The substrate must be cement laitance free, clean and free from dirt, oil, grease or other contaminants and loose or friable particles.
- The substrate must be perfectly flat, sound and free from parts easily removed, non-deformable and correctly aged.
- Any small gradients or bumps can be levelled / filled with a layer of SikaCeram®-288 H in a maximum thickness of 5 mm, applied at least 24 hours before laying the ceramic coating. For builds greater than 15mm thick, use the appropriate Sika MonoTop® or Sika® Level product(s).
- SikaCeram®-288 H is applied directly on plasters and cementitious substrates, cement-lime mortars, concrete, plasterboard, floater finished concrete and old ceramic floors. On other substrates, use relevant primers.

MIXING

- Mix the contents of a 25 kg bag with the required amount of water (as specified above), using an electric mixer and a suitable mixing spiral at low speed, in a clean bucket.
- Do not exceed a mixing speed of 500 rpm as doing so may reduce the final strength of the cured product.
- Mix to obtain a smooth paste free of lumps.
- After mixing, leave the product for 5 minutes, then briefly stir the mixture prior to application. This should result in a very creamy, easily spreadable, and highly thixotropic adhesive.

APPLICATION

- SikaCeram®-288 H is applied using a notched trowel. The amount of product should be enough to ensure complete wetting of the tile.
- Tiling has to be carried out on fresh adhesive, exerting an adequate pressure to ensure contact with the adhesive to form a full bond. If a surface film has formed on the adhesive, it is necessary to trowel over the previously applied adhesive layer.
- Avoid wetting the adhesive already applied with water.
- To lay tiles sized 900 cm² (e.g. 30 x 30 cm) or larger, the double-spreading (buttering) thin-bed consistency or single-spreading flow-bed consistency techniques of adhesive application is always recommended.
- If the substrate is very porous, if the temperature is high and/or the relative humidity low, it is advisable to dampen the surface.
- Do not leave any standing water.

CLEANING OF EQUIPMENT

- Clean all tools and application equipment with water immediately after use.
- Hardened material can only be mechanically removed.

FURTHER INFORMATION

Gypsum plaster substrates must have a minimum thickness of 10 mm and a maximum moisture content of 0.5%.

- If a waterproofing layer under tiles is required, cement and acrylic based membranes are allowed
 - Protect freshly applied material from freezing conditions and rain, etc.
 - Perform a test prior to carrying out any work with natural stone tiles
 - It is not usually necessary to pre-dampen the tiles
- SikaCeram®-288 H shall not be applied in the following cases:
- On metal surfaces and wood
 - On old ceramic tiles outdoor

IMPORTANT CONSIDERATIONS

- All technical data stated in this Product Data Sheet is based on laboratory tests.
- Actual measured data may vary due to circumstances beyond our control.
- Values achieved in laboratory conditions: 23°C ± 2°C – R.H. 50% ± 5%.
- Higher temperatures reduce the indicated lapse time, oppositely, lower temperatures increase them.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA BANGLADESH LIMITED

Skylark MAK 84, 8th floor
House No. 84, Block D, Road No. 11
Banani, Dhaka-1213, Bangladesh
Phone 1: +88 01313095060
Phone 2: +88 01313095061
ind.sika.com

Product Data Sheet

SikaCeram®-288 H
May 2020, Version 01.01
021710102000000349

SikaCeram-288H-en-BD-(05-2020)-1-1.pdf

