

PRODUCT DATA SHEET

Sika® FerroGard®-903

PENETRATING, CORROSION INHIBITING, IMPREGNATION COATING FOR HARDENED CONCRETE

DESCRIPTION

Sika® FerroGard®-903 is a corrosion inhibiting impregnation coating for hardened concrete surfaces. It is designed to penetrate the surface and then to diffuse in vapor or liquid form to the steel reinforcing bars embedded in the concrete. Sika® FerroGard®-903 forms a protective layer on the steel surface which inhibits corrosion caused by the presence of chlorides as well as by carbonation of concrete.

How it works

Sika® FerroGard®-903 is a combination of amino alcohols, and organic and inorganic inhibitors that protects both the anodic and cathodic parts of the corrosion cell. This dual action effect dramatically delays the initiation of corrosion and greatly reduces the overall corrosion activity. Sika® FerroGard®-903 protects the embedded steel by depositing a physical barrier in the form of a protective layer on the surface of the steel reinforcement. This barrier inhibits corrosion of the steel.

USES

Sika® FerroGard®-903 is recommended for all steel-reinforced, prestressed, precast, post tensioned or marine concrete. Use of Sika® FerroGard®-903:

- Steel-reinforced concrete structures above and below ground, bridges and highways exposed to corrosive environments (deicing salts, weathering)
- For repair and maintenance as treatment of (as yet) undamaged reinforced concrete structures where reinforced steel which is corroding, or is in danger of corroding due to the effects of carbonation or chloride attack Building facades and balconies
- Steel-reinforced concrete in or near a marine environment
- Parking garages
- Piers, piles, and concrete dock structures
- As part of Sika's system approach for buildings and civil engineering structures

CHARACTERISTICS / ADVANTAGES

Sika® FerroGard®-903 offers owners, specifiers, port authorities, DOTs, and engineers, a new technology in corrosion inhibition that can easily be applied to the surface of existing concrete to extend the service life of any reinforced concrete structure.

- Protects against the harmful effects of corrosion by penetrating the surface of even the most dense concrete and diffusing to the steel to inhibit corrosion.
- Enhances the durability of reinforced concrete.
- Does not require concrete removal.
- Environmentally sound.
- Does not contain calcium nitrite.
- Easily applied by either spray or roller to all existing reinforced concrete.
- Can be applied to reinforced concrete that already exhibits corrosion.
- Adds additional benefits when used prior to protective coatings in concrete restoration systems.
- Water based for easy handling and application.
- Not a vapor barrier; allows vapor diffusion.
- FerroGard has been proven effective in both laboratory (ASTM G109/Cracked Beams) and field analysis.
- ANSI/NSF Standard 61 potable water approved

APPROVALS / CERTIFICATES

Mott MacDonald, Evaluation of Sika® FerroGard®, Ref. 26'063/001 Rev A April 1996.
Wolfseher & Partner, Materials Technological Investigation, Report No. 96.144.11 and Report No. 98.115.11.

PRODUCT INFORMATION

Packaging	20 kg Container
Appearance / Colour	Transparent liquid
Shelf life	24 months from date of production if stored properly in undamaged and unopened, original sealed packaging. Store in a cool environment.
Storage conditions	Store at 40-95°F (4-35°C). Protect from freezing. If frozen, discard.
Density	~ 1.13 (at +20°C)
pH-Value	11 (±1)
Viscosity	~ 25 cps

TECHNICAL INFORMATION

Penetration Depth	Key Criteria	Performance Level	Test Method/Institute
	Corrosion Inhibition	Sika® FerroGard®-903 corrosion inhibitors delay the onset of corrosion and reduce the rate of corrosion by 65% versus control specimen after 1 year.	1
	Penetration Rate in hardened concrete	Sika® FerroGard®-903 penetrates independently of orientation (horizontal, vertical, overhead) at a rate of 1/10 to 4/5 inches (2.5 to 20 mm) per day, depending on the density of the concrete.	2
	Depth of Penetration	Sika® FerroGard®-903 penetrates up to 3 inches (76 mm) in 28 days.	2
	Protective layer on steel	Sika® FerroGard®-903 forms a protective layer on the reinforcing steel of high integrity measured at as much as 100 Å in thickness	3
	Displacement of chlorides from steel surface	Sika® FerroGard®-903 forms a continuous film on the reinforcing steel and displaces chloride ions from the steel surface.	3
	Corrosion Rate Field Monitoring	Reduction of corrosion rates in excess of 65%.	4

Test Method/Institute:

¹ Cracked Concrete Beam Test (adapted from ASTM G109)

² Secondary Neutron Mass Spectroscopy (SNMS) / Institute for Radiochemistry, Karlsruhe (Germany), Prof. Dr. J. Goschnick

³ X-ray Photon Spectroscopy (XPS) and Secondary Ion Mass Spectroscopy (SIMS) / Brundle and Associates, San Jose, CA and University Heidelberg (Germany), Prof. M. Grunze

⁴ Performance of Corrosion Inhibitors in Practice, Graeme Jones, C-Probe

APPLICATION INFORMATION

Consumption	Generally 0.500 kg/m ² For very dense concrete with low permeability, the rate of application of Sika® FerroGard®-903 can be reduced but must not be lower than 0.300 kg/m ² .
Waiting Time / Overcoating	<p>Number of coats: This is dependent on the porosity and moisture content of the substrate and the weather conditions, normally 3 to 5 coats are necessary to achieve the required consumption.</p> <p>Waiting time between coats: This is dependent on the porosity of the concrete and the weather conditions, normally 1 hour to a few hours to allow the surface to dry between coats.</p> <p>Over coating: Two days (or later) after the application of Sika® FerroGard®-903, the treated surfaces must be washed down once or twice with water and allowed to dry for at least 3 days. Then clean the surface thoroughly by water jet (~100-150 bars) and allow drying for a further 3 days. SikaGard® hydrophobic impregnations or SikaGard® breathable coatings can then be applied - follow the information in the respective product data sheet. Tests have shown good compatibility with most Sika® breathable coatings. If other products are to be applied, please contact the manufacturer's technical department for confirmation of compatibility with Sika® FerroGard®-903.</p> <p>Over coating with cementitious products: Patch repair Allow areas treated with Sika® FerroGard®-903 to dry for a couple of days. Rinse treated surface with high-pressure water jet (~100-150 bars). As a bonding agent for cementitious repair systems, only SikaTop® Armatec-110 Epocem® is to be used (follow the information in the product data sheet).</p>

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Before applying Sika® FerroGard®-903 be sure the surface is clean and sound. Remove all dirt, dust, oil, grease, efflorescence or existing coatings from concrete surface by steam cleaning, water blasting or slightly sandblasting (Do not use hot water). Allow concrete surface to dry prior to application of Sika® FerroGard®-903. The dryer the surface the better the penetration and effectiveness.

APPLICATION

Sika® FerroGard®-903 is applied by roller, brush or spray on concrete surfaces. When spraying, use a conventional airless spray system or hand-pressure equipment. **A minimum of two coats is always recommended.** Dense substrates may require more coats. Waiting time between coats of Sika® FerroGard®-903 is at least 1 hour. Allow a minimum of one day to allow Sika FerroGard 903 to dry and penetrate. When Sika® FerroGard®-903 is used prior to the application of a repair mortar, concrete overlay, protect-

ive coating, Sikafloor system or any other application, care must be taken to remove any residue remaining on the surface from the application of Sika® FerroGard®-903. Clean the substrate in such a manner (i.e. push the water in one direction away and off from the surface to be overcoated) to completely remove any residue. Horizontal surfaces require pressure washing (~100-150 bars) to remove the residue. Vertical surfaces may be rinsed with water or pressure washed. The use of Sika Armatec 110 EpoCem as a bonding agent prior to the application of repair mortars or concrete overlays is suggested. Drying times depend on environmental conditions, absorbency of the substrate and maximum recommended moisture content for the subsequently applied system.

Curing Treatment

Sika® FerroGard®-903 does not require any special curing but must be protected from rain for at least 6 hours at +20°C.

CLEANING OF EQUIPMENT

Use water to clean application equipment etc.

IMPORTANT CONSIDERATIONS

- Minimum ambient and substrate temperatures 35 °F.
- Do not apply when temperature is expected to fall below 35 °F within 12 hours.
- Do not apply where there is expected rain or frost.
- If the applied surfaces will be submerged after the application of Sika® FerroGard®-903, a waterproofing coating must be applied prior to submersion.
- Substrate should be as dry as possible prior to the application.
- Protect glass, wood, brick, galvanized steel, copper and exposed aluminum during the application.
- Maximum chloride content of concrete structures intended to be treated with Sika® FerroGard®-903 is 6 lbs./y³ (measured at the level of the reinforcing steel). For levels up to 10 lbs./y³, consult technical service.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA BANGLADESH LIMITED

Skylark MAK 84, 8th floor
House No. 84, Block D, Road No. 11
Banani, Dhaka-1213, Bangladesh
Phone 1: +88 01313095060
Phone 2: +88 01313095061
ind.sika.com

Product Data Sheet
Sika® FerroGard®-903
January 2020, Version 01.01
020303040010000001

SikaFerroGard-903-en-BD-(01-2020)-1-1.pdf

