

PRODUCT DATA SHEET

Sika® ViscoCrete® ACE 30 JP

High range water reducing/ super plasticizing, admixture for precast and high performance concrete

DESCRIPTION

Sika® ViscoCrete® ACE 30 JP is an admixture of a new generation based on second-generation polycarboxylic ether polymer with high early strength gains. It is free of chloride & low alkali. It's compatible with all kinds of cements.

USES

- Suitable for making precast concrete elements at all work-abilities including Rheo-plastic or Super Workable Concrete having fluid consistency, no segregation, a low water binder ratio and consequently high early and ultimate strengths.
- As a component of Zero Energy System.
- Concreting in cold weather.

FEATURES

- Achieve high early strengths.
- Produces Rheo-plastic and Rheo-dynamic concretes having a low water binder ratio.
- Optimize curing cycles by reducing curing time or curing temperatures.
- Eliminate heat curing.
- Eliminate the energy required for placing, compacting & curing (Zero Energy System).
- Increase productivity/ reduction in cycle time.
- Improve surface appearance.
- Produce durable precast concrete elements.
- Improved engineering properties, compared to traditional superplasticizer such as early and ultimate compressive and flexural strengths, reduced shrinkage and low permeability.

CERTIFICATES AND TEST REPORTS

Complies with ASTM C494 Type F, EN 934-2 T3.1/3.2, IS 9103:1999

PRODUCT INFORMATION

Composition	Modified Polycarboxylate Ether (PCE)
Packaging	Sika® ViscoCrete® ACE 30 JP is supplied in 225 kg drums or in bulk on request.
Shelf life	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.
Storage conditions	Sika® ViscoCrete® ACE 30 JP must be stored where temperatures do not drop below +5°C. If product has frozen, thaw at +5°C or above and completely reconstitute using mild mechanical agitation. Do not use pressurized air for agitation. Store under cover, out of direct sunlight and protect from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging.
Appearance and colour	Light brown liquid

Density ~1.09 at 25°C

pH-Value ≥ 6

Total chloride ion content Nil

APPLICATION INFORMATION

Recommended dosage

Optimum dosage of Sika® ViscoCrete® ACE 30 JP should be determined in trial mixes. As a guide, a dosage range of 500 ml to 1200ml per 100kg of cementitious material is normally recommended. Because of variations in concrete materials, job site conditions, and/or applications, dosages outside of the recommended range may be required. In such cases, contact your local Sika representative.

Effects of over dosage

A severe over-dosage of Sika® ViscoCrete® ACE 30 JP can result in the following:

- Air entrainment
- Bleed/segregation of mix, quick loss of workability
- Increased plastic shrinkage

A slight overdosing may not adversely affect the ultimate strength of the concrete and can achieve higher strengths than normal concrete, provided it is properly compacted and cured. Due allowance should be made for the effect of fluid concrete pressure on form work, and stripping times should be monitored.

Compatibility

Sika® ViscoCrete® ACE 30 JP may be combined with many other Sika® products. Compatible with all types of cements and cementitious materials.

Important: Always conduct trials before combining products in specific mixes and combinations.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

DISPENSING

Sika® ViscoCrete® ACE 30 JP is a ready-to-use liquid which is dispensed into the concrete together with the mixing water. The plasticizing effect and water reduction are higher if the admixture is added to the damp concrete after 70 to 90% of the mixing water has been added. The addition of Sika® ViscoCrete® ACE 30 JP to dry aggregate or cement is not recommended. Automatic dispensers are available. Thorough mixing is essential and a minimum mixing cycle, after the addition of the Sika® ViscoCrete® ACE 30 JP, of 60 seconds for forced action mixers is recommended.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika re-

serves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA BANGLADESH LIMITED

Impetus Center, 242/B, 8th Floor
Bir Uttam Mir Shawkat Sarak
Dhaka-1208, Bangladesh
Phone 1: +88 01313095060
Phone 2: +88 01313095061
bgd.sika.com

Product Data Sheet
Sika® ViscoCrete® ACE 30 JP
May 2024, Version 01.01
021301011000005503

SikaViscoCreteACE30JP-en-BD-(05-2024)-1-1.pdf

